

Eco-Friendly Holographic Film for Sustainable and Eye-Catching Packaging Designs

Basic Information

Place of Origin: Zhejiang, ChinaBrand Name: ZHANXIN

• Minimum Order Quantity: 10000 square meters


• Price: \$0.37/square meters 10000-29999 square

meters

Packaging Details: Carton, Pallet.

Supply Ability: 100000 Square Meter/Square Meters per

Month



Product Specification

Industrial Use: Gift & Craft

• Use: Other Gift & Craft, Packaging Film

Material: PLA Film

Type: Holographic FilmFeature: Water Soluble

Hardness: SoftProcessing Type: CastingTransparency: Transparent


• Product Name: 100% Degradable And Environment-Friendly

Holographic Package Film

• Size: Custmozied

MOQ: 10000 Square MeterWidth: 510 Mm, 1020 Mm

Length: 3000 MPort: Ningbo



More Images












Product Description


100% Degradable and Environment-friendly Holographic Package Film

BOPLA Film Layer Structure









Product Features

- ${\tt \odot} \ {\tt The \ biological \ material \ is \ soluble \ and \ degradable, \ which \ is \ environment-friendly \ and \ has \ low \ carbon \ emission.}$
- $\ensuremath{\circ}$ Biodegradable into carbon dioxide, water and biomass by microbial digestion.
- \circ Consistent surface energy for good printability.
- \circ Good heat sealing perfomance, can be directly heat sealing without glue.
- \circ Excellent transparency and gloss, lower haze.
- \circ Excellent processing performance, good folding form stability and twisting retention.

Typical Properties		Test Method	Units	Typical Value
Thickness		-	μm	15
Average Thickness Tolera	nce			
Tensile Strength	MD	ASTM d882	MPa	135
	TD			130
Elogation at Break	MD	ASTM D882	%	100
	TD			90
Heat Shrinkage	MD	ASTM D1204		406
Heat Shillikaye	TD	(100°C, 10min)		3.5
Dynamic COF	Untreated Side	ASTM D1894	-	0.5
	Treated Side			42
Surface Tension	Untreated Side	ASTM D2578	mN/m	34

Haze	ASTM D1003	%	4.5
Light Transmission	AS INI D 1003		94
Gloss(angle 45°)	ASTM D2457	%	80


- Remark:


 1. Testing Conditions: 20°C, 65%RH (except as otherwise provided in the test method)

 2. The property values represented in the table do not constitute product specifications, but represent the average or typical values.

Product Applications

Food packaging Candy packaging Cardboard Boxes Label







Wenzhou Zhanxin New Materials Technology Co., Ltd.

+8613736302979



sales@holographic-film.com



holographic-film.com

No.1, Mocheng Industrial Zone, Aojiang Town, Pingyang County, Wenzhou City, Zhejiang, China